

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 11-093827
 (43)Date of publication of application : 06.04.1999

(51)Int.Cl.

F03G 7/00

(21)Application number : 09-253870

(71)Applicant : TOSHIBA CORP

(22)Date of filing : 18.09.1997


(72)Inventor : HIRAOKA TOSHIRO
 ASAKAWA KOUJI
 HAYASE SHUJI
 MAEDA KATSUHIRO

(54) FUNCTIONAL ELEMENT AND ACTUATOR

(57)Abstract:

PROBLEM TO BE SOLVED: To provide a functional element which has the large interface area and has high durability of an interface by forming a three-dimensional co-continuous micro phase separating structure of a semiconductive or conductive organic high polymer chain and an ion conductive organic high polymer chain, and using a high polymer mold chemically bonded on the interface.

SOLUTION: A material by bonding a light electric charge generating or carrier transporting molecular structure in a pendant shape in a principal chain or as a side chain of an electrically inactive high polymer chain, can be cited as a semiconductive or conductive organic high polymer. A conjugative high polymer may also be used. A high polymer electrolyte type ion conductor can be cited as an ion conductive high polymer. A phase separating film 103 is formed by applying a diblock copolymer of polyaniline (basic emeraldin)- polyethylene oxide on a transparent electrode 102 formed on a glass substrate 101. A carbon electrode 105 is arranged on this through an electrolyte phase 104. An electrochromic element manufacture in this way has a high response speed.



LEGAL STATUS

[Date of request for examination] 06.09.2000

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right]

Copyright (C); 1998,2003 Japan Patent Office